

Volume 6 Issue 04

Title	STUDY ON HARDNESS AND WEAR RESISTANCE OF LAYERS OVERLAYED USING ELECTRODES WITH NANO-MODIFIED COATING	
Author	PLAMEN TASHEV, HRISTO KONDOV, ELISAVETA TASHEVA, MARA KANDEVA .	
Source	International Journal of Engineering and Applied sciences pp 01 - 06 Vol 06. No. 04, 2015	
Abstract	Developed is innovative manufacture technology for electrodes nano-modified with TiN, Al2O3, SiC, TiCN+C, TiN+Cr, and TiCN purposed for weld overlay of wear resistant surface layers. Test samples are cladded using the manufactured electrodes. Vickers hardness and wear resistance of the overlayd metal are measured	
Keywords	electrode, manual arc welding, nano-modifier, weld overlay, overlayed layer, Vickers hardness, wear resistance .	
	Click here for full Text	

Title	PROCESSING OF LOW-CYCLE FATIGUE TESTS DATA ON A BASE OF KINETIC FATIGUE THEORY
Author	SYZRANTSEV V.N., SYZRANTSEVA K.V., ILINYKH V.N.
Source	International Journal of Engineering and Applied sciences pp 07-10 Vol 06. No. 04, 2015
Abstract	To describe the results of tests of samples destruction in a field of low-cycle deforming authors use mathematical model developed in the kinetic theory of mechanical fatigue. Two additional parameters were included in developed model. First parameter characterizes the initial damage of part material, which exists before cyclic deforming of part. Second parameter describes the part resistance against the growth of fatigue cracks. Proposed earlier methods of experimental determination of these parameters values in real operational tests of parts do not allow to obtain required information. The paper considers the task of calculation of these parameters based on results of sample's longevity tests and developed mathematical model
Keywords	tensile strength, cyclic deforming, low-cycle fatigue, damages accumulation
	<u>Click here for full Text</u>

Title	EQUIVALENCE AMONG VISCOELASTIC SPRING-POT GENERAL PROCESSES AND A PURE VISCOUS NEWTONIAN SYSTEM OBSERVED ON A TIME SCALE	
Author	LUCIANO BARBANTI, BERENICE DAMASCENO	
Source	International Journal of Engineering and Applied sciences pp 11 - 14 Vol 06. No. 04, 2015	
Abstract	The use of fractional calculus when modeling phenomena frequently suggests several questions concerning the deepest parts of the physical laws involved in. Here we will be dealing with one instance of such situation. We will be showing that a very large class of viscoelastic systems are equivalent to a pure viscous (Newtonian) process observed in a discrete time scale.	
Keywords	Spring-pot, fractional derivative, derivative on time scales, Hookean elasticity, Newtonian pure viscosity.	
	Click here for full Text	

Title	Spring-pot, fractional derivative, derivative on time scales, Hookean elasticity, Newtonian pure viscosity.	
Author	ITTAM, A. ESSIEN AND INYANG,D. OKON	
Source	International Journal of Engineering and Applied sciences pp 15 - 27 Vol 06. No. 04, 2015	
Abstract	Granulometry and pebble morphometry was carried out in the studying of depositional environment of Awi Sandstone of the Calabar Flank. Granulometric analysis of 15 samples show the formation has a graphic mean (MZ) of 0.89?, average sorting coefficient (sI) of 1.31?, Skewness (Ski) is positively skewed and kurtosis (KG), ranges from platykurtic to leptokurtic ranges. Pebble morphometric analysis of the conglomerates (360 pebbles) from 10 locations showed that the mean values of various morphometric ranges as follows: flatness ratio (FR = 0.52-0.59),	
Keywords	Granulometry, pebble morphometry, Awi Sandstone, bivariate plots, environment of deposition	

Title	FORMULATION AND EVALUATION OF FAST DISSOLVING ORAL FILMS OF METOPROLOL SCCINATE	
Author	DR. D. NAGENDRAKUMAR, KESHAVSHETTI GG, PRATIBHA MOGALE, SWATI SWAMI*, HARSHANAND SWAMI	
Source	International Journal of Engineering and Applied sciences pp 28 - 38` Vol 06. No. 04, 2015	
Abstract	Fast dissolving oral films are useful in patients such as paediatric, geriatric, bedridden or developmentally disabled who face difficulty in swallowing conventional tablets or capsules and liquid orals or syrups leading to ineffective therapy. The delivery system consists of a very thin oral strip, which is simply placed on the patient's tongue or any oral mucosal tissue, instantly wet by saliva the film rapidly hydrates and adheres onto the site of application	
Keywords	HPMC E-5, HEC, Oral Films, Metoprolol Succinate, Solvent Casting Method	
	Click here for full Text	

Volume 6 Issue 03

Title	CHARACTERIZATION OF MATERIALS FROM ABA WASTE DUMPSITES	
Author	UKPONG, E. C; UDO, E. A., AND UMOH, I .C .	
Source	international Journal of Engineering and Applied sciences pp 01 - 10 Vol 06. No. 03, 2015	
Abstract	The leachate quality from two major dumpsites in Aba (Umuigwe Osisioma and Ogbor) was analysed for its physiochemical parameters. Standard methods for analysis of physiochemical parameters were used in this assessment. It was realized that leachate from both dumpsites had high Biological Oxygen Demand (BOD) of (65mg/l), ammonia (32.15mg/l), sulphates	
Keywords	Leachate, dumpsites, Umuigwe Osisioma, Ogbor, BOD Concentration	



. . . 0

ABOUT THIS JOURNAL	
About EAAS	
Scope of Journal	
Abstracting & Indexing	
EAAS CALL FOR PAPERS	
Call For Papers	
Submission Guidelines	
Review Process	
Submit Manuscript	
EDITORIAL BOARD	
View Full Editorial Board	
SUBSCRIPTION	
Publication Charges	
Subscription Information	

For sister journals please visit <u>WWW.IJSK.0rg (IJSK-IJRSS-IJRHS-IJRAFS-IJREES</u> ISSN 2305-8269

International Journal of Engineering and Applied Sciences

International Journal of Engineering and Applied Sciences (EAAS) is dedicated in integrating publications that have expansion and research outcomes within the extensive spectrum of subfields in the applied sciences and engineering. The journal is issuing scientific study concerning to various disciplines of the applied sciences and engineering fields from hypothetical, applied and analytical study to practical inferences and academic or quantifiable discussion envisioned for both academic and business progress. EAAS is a peer review open access journal and objects to deliver scientific information to its readers in the field of applied sciences and engineering

EAAS proposed audience is encompassed of scientists, researchers, professionals. EAAS welcomes them all to publish their study in their specific area.

Invitation for Publication

Scope of Journal

Editorial Board

EAAS comprehends the status of research work of authors, so it is highly desirable to uphold professional and highly constructive association with reviewers and editorial team, who help us to evaluate the manuscripts and give the fair opinion to authors. We select only highly competent people in our editorial team because highest standard of research publication can only be achieved by help of those who have passion for conducting and reviewing research.

Editorial Board (List Updation Is in process)

1. **Prof. Dr. Charles Christopher Sorrell**, School of Material Sciences and Engineering, University of New South Wales, Sydney, Australia

- 2. Dr. Ebru Aydeniz, Department of Architecture, Yasar University, Turkey
- 3. Dr. Badam Singh, Department of Applied Mathematics, Indian School of Mines, India
- 4. Dr. Ideisan Ibrahim, Department of Chemistry, University Of Sharjah, UAE
- 5. Dr. Sanjeev Kumar, Department of Electronics Engineering, Indian School of Mines, India
- 6. Dr. Bilal A. Akash, Department of Mechanical Engineering, Dhofar University, Oman
- 7. Dr. Prasanta K. Jana, IEEE Senior Member, USA
- 8. Dr. Hari Om, Department of Computer Science and Engineering, Indian School of Mines, India

9. **Dr. Yalin Kilic TUREL**, Department of Computer Education and Instructional Technologies, Firat University, Turkey

10. Dr. Shiv Datt Kumar, Department of Mathematics, Motilal Nehru National Institute of Technology, India

11. **Dr. Mohd Idrus Mohd Masirin**, Faculty of Civil and Environmental Engineering, Universiti of Tun Hussein Onn Malaysia, Malaysia

12. Dr. Murat Egi, Department of Computer Engineering, University Galatasaray, Turkey

13. Dr. Khalid Farhod Chasib, Department of Chemical Engineering, University Of Technology, Iraq

14. Dr. Leila Ismail, College of Information Technology, United Arab Emirates University, UAE

15. Dr. Saranjit Singh, School of Mechanical Engineering, KIIT University, India

16. Assoc. Prof. **Dr. Zuhailawati Hussain**, School of Materials & Minerals Resources Engineering, Universiti Sains Malaysia

17. Dr. Hakan Cetinel, Department of Mechanical Engineering, Celal Bayar University, Turkey

18. Dr. Lalit Kumar, Department of Mathematics, university of Delhi, India

19. Dr. Masoud Hajarian, Department of Mathematics, Shahid Beheshti University, Iran

20. Dr. Reza Shariatinasab, Deparment of Electrical and Computer Engineerning, University of Birjand, Iran.

21. Dr. Abdul Mutalib leman, Faculty of Engineering and Technology, Universiti Tun Hussein Onn, Malaysia

22. **Dr. Jyotindra C. Prajapati,** Department of Mathematical Sciences, Faculty of Applied Sciences, Charotar University of Science and Technology, India

23. Dr. Mohammad Mehdi Rashidi, Department of Mechnical Engineering, Bu-Ali Sina University, Iran

24. **Dr. Tamer Medhat Mohammad Ibrahim**, Electrical Engineering Department, faculty of Engineering, Kafrelsheikh University, Egypt

25. **Dr. Mohammad Hadi Dehghani,** Department of Enviornmental Health Engineering, School of public Health, Tehran University of Medical Sciences, Iran

26. **Dr. Hardeep Singh**, Department of Electronics and Communication Department., Indo Global College of Engineering, India

27. Dr. Atmani Hassan, Director of Organization Entraide Nationale, Morocco

28. Dr. Nguyen Huy Tuan, Department of Mathematics and Informatics, University of Natural Sciences, Vietnam

29. Dr. Habibolla Latifizadeh, Department of Mathematics, Shiraz University of Technology, Iran

- 30. Dr. TAN CHEE FAI, Faculty of Mechanical Engineering, Universiti Teknikal Malaysia Melaka, Malaysia
- 31. Dr. Venugopal Thottempudi, Department of Chemistry, University of Idaho, USA

32. Dr. T.V Surya Naryana, Department of Electronics and computer Engineering, K L University, India

33. Dr. Dae San Kim, Department of Maths, Sogang University, Korea

34. Dr. Ching-Sung Wang, Electrical Engineering, Oriental Institute of Technology, Taiwan

35. **Dr. Krastanov Krasimiri**, Department of Material Handling and Construction Machines, Todor Kableshkov University of Transport Education, Bulgaria

36. Dr. Abdelhalim Ebaid, Department of Maths, University of tabuk, Saudia Arabia

37. Dr. Sunil Kumar, Department of Maths, National Institute of Technology, India

38. Dr. Taha Mattar, Steel Technology Department, Central Metallurgical R & D Institute, Egypt

- 39. Dr. K.V.L.N.Acharyulu, Department of Maths, Bapatla Engineering, India
- 40. Dr. Taghreed Hashim Al-Noor, Department of Chemistry, university of Baghdad, Iraq

41. Dr. Kosa Golic, Faculty of Construction Managemetn, University Union Nikola Tesla, Serbia.

42. **Dr. Mohammad Reza Alizadeh**, Department of Agricultural Engineering (Head), The Rice Research Institute of Iran (RRII), Iran.

43. **Dr. Bensafi Abd-El-Hamid**, Department of Chemistry and Physics, Faculty of Sciences, Abou Bekr Belkaid University of Tlemcen, Algeria

44. **Dr. Vishnu Narayan Mishra**, Department of Mathematics, Sardar Vallabhbhai National Institute of Technology, India

45. Dr. Fadhl M. Al-Akwaa, Biomedical Engineering, University of Science and Technology, Sana'a, Yemen

46. Dr. Mohd Zainal Abidin Ab Kadir, Faculty of Engineering, Universiti Putra Malaysia (UPM), Malaysia

47. Dr. Jung-Chang Wang, Department of Marine Engineering, National Taiwan Ocean University, Taiwan

48. Dr. Hesham G. Ibrahim, Faculty of Marine Resources Al-Asmarya Islamic University, Zliten City, Libya

49. **Dr. Mohammad Abedel Samei' Tabieh**, Dep. Of Agricultural Economics and Agribusiness, Faculty of Agriculture, The University of Jordan, Jordan.

50. Dr. Sivakumar Sukumaran, Agronomy: Plant Breeding & Genetics, Kansas State University, USA.

51. Dr. Arda YILDIRIM, Faculty of Agriculture, Department of Animal Science, Gaziosmanpasa University, Turkey.

52. Dr. Chee-Ming Chan, infrastructure engineering and geomatic, Universiti Tun Hussein Onn Malaysia, Malaysia.

53. **Dr (Eng). G.G. Tushara Chaminda**, Department of Civil and Environmental Engineering, Faculty of Engineering, University of Ruhuna, Hapugala, SRI LANKA.

54. Dr. Sylwia Myszograj, Faculty of Civil and Enviornmental Engineering, University of Zielona Gora, Poland.

Abstracting and Indexing

- 1- Directory of Open Access Journals (DOAJ)
- 2- OpenJ-Gate
- 3- Academic Journals Database
- 4- ScientificCommons
- 5- Microsoft Academic Search
- 6- Academic Index
- 7- CiteSeerX
- 8- <u>RefSeek</u>
- 9- <u>ISEEK</u>
- 10- <u>Socol@r</u>
- 11- ResearchGATE
- 12- Libsearch
- 13- Bielefeld Academic Search Engine (BASE)
- 14- Google Scholar
- 15- Indexed in <u>Electronic Journals Library</u>
- 16- Indexed in : DRJI





STUDY ON HARDNESS AND WEAR RESISTANCE OF LAYERS OVERLAYED USING ELECTRODES WITH NANO-MODIFIED COATING

PLAMEN TASHEV, HRISTO KONDOV¹, ELISAVETA TASHEVA², MARA KANDEVA³

Institute of Metal Sciences, Equipment and Technologies "Acad. Angel Balevski" with Hydroaerodynamics Centre 63, Shipchenski prohod, 1574 Sofia, Bulgaria¹ Higher School of Transport T. Kableshkov, Bulgaria 1574, Sofia, 158Geo Milev² Technical University of Sofia, Sofia 1000, 8 Kl. Ohridski Blvd³

ABSTRACT

Developed is innovative manufacture technology for electrodes nano-modified with TiN, Al_2O_3 , SiC, TiCN+C, TiN+Cr, and TiCN purposed for weld overlay of wear resistant surface layers. Test samples are cladded using the manufactured electrodes. Vickers hardness and wear resistance of the overlayd metal are measured The resulting variations of hardness and wear resistance are analyzed in relation with the nature of nano-modifier used. The application area of nano-modified electrodes is for both preventive and repair weld overlay.

Key words: electrode, manual arc welding, nano-modifier, weld overlay, overlayed layer, Vickers hardness, wear resistance

INTRODUCTION

Arc welding is a technology appropriate to increase the wear resistance of surfaces of parts and tools. The weld overlay can be purposed for prevention or repair. The process is especially efficient when different modifying additives are introduced in the weld overlay metal. The additives can be introduced via the coating of the welding electrodes.

The recent study presents an innovative technology for manufacture of electrodes for arc manual welding containing different types of nano-particles (modifiers) in the coating. Herein are also presented the results from the testing of hardness and wear resistance of claddings overlayed using nano-modified electrodes.

The review of the reference literature available reveals numerous studies on the effect of titanium-containing nano-particles on the technical characteristics of the metal after weld overlay. Most studies use titanium dioxide, titanium, titanium carbonitride [1],and silicon carbide [2] as nano-modifiers. It is found that the increased quantities of titanium-containing inclusions lead to changes in the micro-structure of the metal thus improving its mechanical properties (hardness, wear resistance) [3]. The increased concentration of titanium in the weld overlayed metal increases the concentration of titanium in these inclusions too. [4]. Examined is the effect of titanium [5] on the properties of the weld overlayed metal at 1.4% and 2% levels of manganese. The mechanical properties of the weld overlayed metal are improved [6-10], especially at medium concentrations of nano-particles, which is explained with the increased level of acicular ferrite and the finer microstructure.

The significantly improved mechanical properties, such as high hardness and toughness, are probably due to the fine grain microstructure and redistribution of internal stresses resulting from the added substances in the form of nano-powders with predominant particle size distribution measuring several tens of nanometers [11,12].

International Journal of Engineering and Applied Sciences © 2012 - 2015 EAAS & ARF. All rights reserved www.eaas-journal.org

for the particular diameter. The first and the last electrode are removed because since their coating is usually incomplete or uneven (Fig. 2).



Fig. 2. Extrusion line

The ready electrodes are arranged on grids and are dried in air and in drying furnace.

The classification of nano-modified electrodes according to the amount and the type of nano-modifier is shown in Table 1.

Sample	Nano modifier	Quantity,
No		%
1	Reference electrode	-
	(IZA-E300)	
2	TiN	А
3	Al_2O_3	А
4	SiC	А
5	TiCN+C (coated	А
	with carbon)	
6	TiN+Cr (coated	А
	with chromium)	
7	TiN	A/2
8	TiCN	A/2
9	Al ₂ O ₃	A/2
10	SiC	A/2
11	TiN+Cr (coated	A/2
	with chromium)	
where	A is the basic qua	antity of nan

Table 1. Classification of electrodes

DEVELOPMENT AND MANUFACTIRE OF NANO-MODIFIED ELECTROLDES FOR WELD OVERLAY

The nano-modified electrodes for weld overlay are developed based on electrode type IZA-E300. It belongs to the group of electrodes for weld overlay of layers with higher requirements for wear resistance. [13]

Materials for the coating of the electrodes delivered are graded according to the technical requirements for each of them individually. Preliminary chemical analysis and granulometric analyses are carried out. Used is potassium water glass with content as per the requirements of the technical specification. Selected is electrode wire with diameter Ø3.25 and length 450mm.

The materials are dosed in accordance with the formulation for manufacture of electrodes type IZA-E300. Nano-materials are input at a certain point in the implementation of the technology, taking into account the specific particle size of material.

The dry homogenization is carried out manually with a blender. The nano-materials for each sample are added immediately before blending. The wet homogenization is carried out in "S" blender with volume up 2,5 kg.

First, the sample coating is dry blended, and then water glass is added in trickle. The coating thus prepared is poured into a suitable container and fed to the extrusion press.

The technological extrusion press (Fig.1) is set for electrodes with dimensions \emptyset 3.25/450 mm.



Fig. 1. Process of extrusion

The extruded electrodes are passed through the trimming device. The concentricity of the coating is checked using a tool that is calibrated modifier used.

EXPERIMENTAL STUDY OF LAYERS WELD OVERLAYD USING NANO MODIFIED ELECTRODES

The characteristics of the experimental nanomodified electrodes are assessed on steel S 235JR plates with dimensions 250x400x20mm (according to Specification ISO/DIS 15614-7 for weld overlay) with three-layer weld overlay cladding.

Assessment of hardness of the weld overlayed metal

After weld overlay, half of the overlayed surface (OS) is polished, as is shown in Fig. 3.



Fig. 3. Cladded and polished sample

The hardness measurements are carried out according to Vickers $HV_{15/15}$ in eight points as per the diagram shown in Fig. 4.



Fig. 4. Diagram of points for measurement of hardness

The maximum deviations from the measured values are eliminated and the average measured values of hardness are shown in Table 2.

Sample	Average value of	
No	hardness HV _{15/15} .	%
11	644.9	56
10	570.6	38
2	485.9	18
6	476.0	16
7	462.0	12
3	436.1	6
8	428.1	4
9	427.9	4
4	412.4	0
1	412.1	0
5	371.1	-10

Estimated is the percentage change of hardness of each sample related to the basic Sample No 1. The highest percentage increase (56%) is achieved in Sample No 11 where the nano-modifier introduced with the coating of the electrode is titanium nitride coated with chromium.

There is a substantial increase of hardness (38%) achieved in Sample No 10 where the nanomodifier introduced is silicon carbide. Most samples (No 9, 8, 3, 7, 6, 2) with nano-modified overlayed surface also exhibit increased hardness in the range from 4% to 18%.

The variations of the average hardness depending on the type of nano-modifier introduced is shown in Fig. 5.



Fig. 5. Vickers hardness of OS depending on the type and the concentration of nano-modifier introduced

Some experimental results for hardness of samples with weld overlayed nano-modified surfaces are presented in [14]. There is a certain

International Journal of Engineering and Applied Sciences © 2012 - 2015 EAAS & ARF. All rights reserved www.eaas-journal.org



dissipation of the measured values for hardness. The comprehensive ultrasound examinations proved that there are a lot of imperfections in the weld overlayed layer that can explain the dissipations of the values for hardness, and in the performance of the cladded layer, respectively.

The authors attempted to diagnose the discontinuities using surface wave method similar to that described in [15]. Registered is a significant deviation from the behavior of the wave and is suggested transformation of Rayleigh wave in another type of wave. The subsurface imperfections can inflict local deformations at significant contact interactions. They can cause dissipation of measurement results when the wear of the overlayed layers is assessed in the recent study.

Assessment of wear resistance of the weld overlayed metal

The authors assess the wear resistance of claddings using our own methodology described in [16, 17]. It consists in measurement of the mass wear of samples after a number of wear cycles and estimation of wear intensity and wear resistance for the travelled path of friction. The comparison upon the parameter wear resistance is made under invariable test conditions.

The methodology for testing of wear resistance is based on measuring the integral (total) loss of mass of the test sample at exactly the same conditions of contact interaction of the sample with the abrasive surface: normal loading, sliding speed, contact area, road of friction, dimension and hardness of abrasive particles. By measuring the mass wear using the developed methodology are estimated the rate of mass wear and the intensity of mass wear resistance.

The samples for the testing of wear resistance are cylindrical with diameter 8mm and length equal to the thickness of the cladded plate. The cylinders are cut out using water jet abrasive technology in order to avoid any possible deformations and stresses from undesired heating. The method for testing is implemented using the device shown in Fig. 8, which operate under kinematic scheme "finger-disc" [23].



Fig.8. Scheme of tribotester for fixed abrasive wear study of coatings

The results from the testing for wear resistance are shown in Table 2. As is seen, the best results are achieved in Sample 11 where the increased hardness (with 56% compared to the reference sample) leads to almost 70% increase of wear resistance. Samples 7, 8, and 10 exhibit wear resistance close to that of the reference sample. The rest samples 2, 3, 4, 5, 6, and 9 exhibit lower wear resistance compared to the reference Sample 1.

Table . Test results of wear resistance

Sample	Wear m,	Wear resistance I_h
No	mg	
1	110.5	$0.44.10^{6}$
2	146.4	$0.33.10^{6}$
3	112.7	$0.43.10^{6}$
4	139.5	$0.35.10^{6}$
5	131	$0.37.10^{6}$
6	138.6	$0.35.10^{6}$
7	97.9	$0.49.10^{6}$
8	92.2	$0.52.10^{6}$
9	125	$0.40.10^{6}$
10	94.4	$0.51.10^{6}$
11	64.4	$0.75.10^{6}$

Figure 9 illustrates graphically the results from testing for wear resistance of weld overlayed layers using nano-modified electrodes.





Fig. 9. Wear resistance of overlayed layers using nano-modified electrodes

CONCLUSIONS

1. Developed is innovative technology for manufacture of nano-modified electrodes for manual arc welding belonging to the group of electrodes for weld overlay of wear resistant surface layers, and trial amounts thereof are manufactured in experimental conditions.

3. Manual arc welding of steel plates S 235JR has been carried out. The welded samples are polished and Vickers hardness is measured.

4. A significant increase of hardness, correspondingly with 56% and 38%, is observed in Samples No 11 and No 10, compared to the reference sample. The overlayed metal in Sample No 11 is nano-modified with titanium nitride coated with chrome, and that of Sample No 10 is nano-modified with silicon carbide.

6. Comparative study of samples for wear resistance is carried out using the method of accelerated surface wear with fixed abrasive. The highest wear resistance (70% higher than that of the reference sample) is achieved in the layer overlayed using electrode Sample No 11.

7. There are certain deviations in hardness and wear resistance that are possibly due to the presence of some sub-surface imperfections revealed through ultrasound non-destructive testing.

8. The nano-modification of surfaces through weld overlay with electrodes for manual arc welding results in considerable increase of hardness and wear resistance of the overlayed layers modified with nano sized particles of TiN coated with Cr.

The work is funded by ASME National Innovation Fund under Contract 6IF N_{\odot} 02-35/15.12.2012.

REFERENCES

[1] Artemev, A., G. N. Sokolov, V. I. Lysak. Effect of microparticles of titanium diboride and nanoparticles of titanium carbonitride on the structure and properties of deposited metal, Metal Science and Heat Treatment, Vol. 53, Nos.. 11 – 12, March, 2012.

[2] Jamaati, R., M. R. Toroghinejad, H. Edris. Effect of SiC Nanoparticles on Bond Strength of Cold Roll Bonded IF Steel, Journal of Materials Engineering and Performance, DOI: 10.1007/s11665-013-0650-8.

[3] Fattahi, M., N. Nabhani, M. Hosseini et all.. Effect of Ti-containing inclusions on the nucleation of acicular ferrite and mechanical properties of multipass weld metals, Micron 45 (2013) pp. 107–114.

[4] Bose-Filho, W.W., A.L.M. Carvalho, M. Strangwood. Effects of alloying elements on the microstructure and inclusion formation in HSLA multipass welds, Materials Characterization, 58 (2007), pp. 29–39.

[5] Beidokhti, B., A.H. Koukabi, A. Dolati. Influences of titanium and manganese on high strength low alloy SAW weld metal properties, Materials Characterization, 60 (2009), pp.225– 233.

[6] Fattahi, M., N. Nabhani, M.R. Vaezi, E. Rahimi. Improvement of impact toughness of AWS E6010 weld metal by adding TiO_2 nanoparticles to the electrode coating, Materials Science and Engineering A 528 (2011), pp.8031–8039.

[7] Paniagua-Mercado, Ana Ma., V. M. Lopez-Hirata, H. J. Dorantes-Rosales et all. Effect of TiO2-containing fluxes on the mechanical properties and microstructure in submerged-arc weld steels, Materials Characterization 60 (2009), pp.36–39.

[8] Beidokhti, B., A.H. Koukabi, A. Dolati. Effect of titanium addition on the microstructure and inclusion formation in submerged arc welded HSLA pipeline steel, Journal of Materials Processing Technology, 209 (2009), pp.4027– 4035.

[9] Tashev, P. M. Kandeva, P. Petrov, An investigation on the wear properties of carbon steel coated with nanoparticles using electron beam technique, Journal of the Balkan

Tribological Association, 2014, ISSN 1310-4772, SciBulCom Ltd., vol. 20, № 2, pp 227-234. [10] Cuixin, C., P. Huifen, L. Ran et all. Research on Inclusions in Low Alloy Steel Welds with Nano Alumina Addition, Journal of Computational and Theoretical Nanoscience, Vol. 9, № 9, Sept. 2012, pp. 1533-1536(4). [11] Черепанов А.Н. и др. "О применении нанопорошков тугоплавких соединений при сварке и обработке металлов и сплавов", Тяжелое машиностроение. №4/2. 2008. С. 25-26 [12] Z.Zhang, D.L.Chen "Consideration of Orowan strengthening effect in particulatereinforced metal matrix nanocomposites:A model for predicting their yield strength" ScriptaMaterialia 54 (2006) 1321-1326 [13] П. Ташев, Х. Кондов, Я. Лукарски, Е. Ташева, "Разработване на наномодифицирани електроди за ръчно електродъгово наваряване, твърдост на наварения слой", Четвърта национална конференция с международно участие "Металознание, хидрои аеродинамика, национална сигурност '2014", 23-24 октомври 2014 г., София [14] KOLAROV I., P. TASHEV. ULTRASONIC STUDY OF OVERLAID NANOMODIFIED LAYERS. International Journal of Engineering and Applied Sciences. Jan. 2015. Vol. 6. No. 01, www.eaas-journal.org. (ISSN2305-8269). [15] Kolarov I. NON-DESTRUCTIVE TESTING OF SURFACE DEFECTS BY RAYLEIGH [16] Mara Kandeva, Boryana Ivanova, Abrasive [17] Ilyan Peichev II., Mara Kandeva, Emilia

WAVE. International virtual journal for science. technics and innovations for the industry. YEAR VIII ISSUE 3 / 2014. SCIENTIFIC TECHNICAL UNION OF MECHANICAL ENGINEERING. www.mech-ing.com/journal. (ISSN 1313-0226).

Wear And Wear-Resistance Of High Strength Cast Iron Containing Sn Microalloy International Journal of The Balkan Tribological Association, 4, Vol. 4, 2013, pp 559-547

Assenova, Vyara. Pojidaeva, About the Deposition of Superilloys by Means of Supersonic HVOF Process, Journal of the Balkan Tribological Association, № 3, Vol.17, 2011 pp 380-386.

V.Petkov. P.Tashev. N.Gidikova. [18] M.Kandeva, R.Valov, "Wear Resistant Chromium Coating With Diamond Nanoparticles upon an Arc Deposited Layer ", Journal of the Balkan Tribological Association 2015, ISSN 1310-4772, SciBulCom Ltd., vol. 25, №1